		Specification		
		HDPE Micro Duct 8/6mm	Docu No. Ver. Date	SKSPEC-MD0806 A June 10, 2017
Test	Characteristic	Test Method	Acceptance Criteria	
Raw	Materials			
1	Micro duct is manufactured	with 100% virgin HDPE		
2	Melt flow index	ASTM 1238 190℃ @ 2.16KG Load	≤ 0.40 g/10min	
3	Density	ASTM D792	$0.940{\sim}0.958{ m g/cm}^3$	
4	Environmental stress crack resist (F50)	ISO 4599	Min. 96h	
Physi	cal and Mechanical Properties	5		
1	Visual appearance	Visual inspection	Ribbed inside & smooth outside surface, free from blisters, shrink hole, flaking, scratches & roughness.	
2	Outer diameter	Seako	8.0mm ± 0.1mm	
3	Wall thickness	Seako	1.00mm ± 0.10mm	
4	Inner diameter clearance	Blowing steel ball	A 4.0mm steel ball can be blown freely through the duct.	
5	Ovality	Seako	≤ 5%	
6	Pressurization	5 minutes @16bar each duct	No damage and leakage	
7	Kink	IEC 60794-1-2 Method E10	≤ 80mm	
8	Tensile strength	Rate of extension: 100mm/min	≥ 385N	
9	Crush	Sample length: 250mm Load: 600N Duration of Max. load: 1 min Recovery time: 1 hour	No residual deformation > 15% of inner and outer diameter, shall pass inner diameter clearance test.	
10	Impact	IEC 60794-1-2 Method E4 1.0 J Impact, recovery time 1 hour	No residual deformation > 15% of inner and outer diameter, shall pass inner diameter clearance test.	
11	Heat reversion	110°C $\sim$ 23°C, 1 hour	≤ 3%	
12	Min. bend radius	100mm	No residual deformation > 15% of inner and outer diameter, shall pass inner diameter clearance test.	
13	Co-efficient of Friction	750mm Diameter, 450°loop, 5kg mass	≤ 0.1	
14	Color and printing	Visual inspection	As per custom	er specification

Completed packages of the HDPE micro duct on drum can be stored outdoor max. 6 months upon the date of production.

Storage temperature:	-40°C	$\sim$	+70°C
Installation temperature:	-30°C	$\sim$	+50°C
Operating temperature:	-40°C	$\sim$	+70°C